

## NATURAL RECLAIM RUBBER

TECHNICAL DATA	Test Method	Nature Reclaim Rubber HTR
<b>CHEMICAL PROPERTIES</b>		
Acetone-Extract %	ASTM D 297-18	11 ± 4
Ash %	ASTM D 297-18	20 ± 7
Carbon Black %	ASTM E 1131	20 ± 7
RHC %	ASTM E 1131	42 Min.
<b>PHYSICAL PROPERTIES</b>		
Specific Gravity (gm / cc)	ASTM D 297-93	1.25 ± 005
Tensile strength (kg / cm <sup>2</sup> )	ASTM D 412	35 Min.
Elongation	ASTM D 412	225 Min.
Mooney Viscosity (1+4)@100'c)	ASTM D 1646	20-50
Hardness at Shore "A"	ASTM D 2240	60 ± 5